



Filter Element: 38-152-60C

| Technical Specification | |
|----------------------------------|--|
| Description | Disposable Coalescing Filter Element |
| Materials of Construction | Borosilicate Glass Microfibres bonded with Kynar fluorocarbon (P.V.D.F.) resin |
| Filtration Efficiency | Better than 99.5+% removal of 0.1 micron particles and aerosols |
| Air Flow Resistance | Less than 1.0KPa at 6 m/min in air at 25°C |
| Dimensions | I.D. - 38.4mm ± 0.25mm |
| | O.D. - 50.0mm ± 1.5mm |
| | Length - 152.0mm ± 0.25mm |
| Strength (dry) | Burst minimum - 5.0 Bar |
| | Collapse minimum - 2.0 Bar |
| Temperature Resistance | -50°C to +150°C maximum in air |
| Chemical Resistance | Resistant to all mineral, vegetable |
| | And synthetic compressor lubricants. |
| | Consult chemical resistance chart for |
| | Other gases and liquids. |

For further specific information please contact our Technical Department
This is a guide only

| | | | |
|--|---|--|--|
| Headline Filters Limited Mill Hall Business Estate Aylesford Kent, ME20 7JZ www.headlinefilters.com info@headlinefilters.com | Filter Element: 38-152-60C | | THE COPYRIGHT OF THIS DRAWING IS RESERVED BY HEADLINE FILTERS. IT IS ISSUED ON CONDITION THAT IT IS NOT COPIED, REPRODUCED OR DISCLOSED TO A THIRD PARTY EITHER WHOLLY, OR IN PART WITHOUT CONSENT IN WRITING. |
| | Material: Borosilicate Glass Microfibres bonded with Kynar fluorocarbon (P.V.D.F.) resin | | |
| DO NOT SCALE DRAWING IF IN DOUBT ASK | | | |